

Property	Symbol	Value	Temperature (°C)	Unit
Initial permeability	μ_i	2400 ± 25%	25	
Saturation magnetic flux density	B_s (mT)	390	100	
Remanence	B_r (mT)	110	25	
Coercivity	H_c (A/m)	13	25	
Core loss	P_{cv} (kW/m³)	600	25	
Core loss	P_{cv} (kW/m³)	300	100	
Curie temperature	T_c (°C)	> 215		
Electrical resistivity	ρ (Ω·m)	6.5		



