




Bs-Temperature

H=1194A/m



Initial permeability	μ_i	25°C	1500±25%
saturation magnetic flux density	B_s (mT)	25°C	530
flux density		100°C	440
Remanence	Br(mT)	25°C	210
		100°C	70
Coercivity	Hc(A/m)	25°C	24
		100°C	13
Core loss	Pcv(kW/m³)	25°C	1000
		100kHz 200mT	100°C
Curie temperature	Tc(°C)		≥285
Electrical resistivity	ρ (Ω·m)		3
Density	d(kg/m³)		4.8×10³

μ_i -Temperature




est. core dimensions (mm)

OD : 25

ID : 15

H : 7.5



frequency

B-H

μ_i -F

