


Initial permeability	$\mu_i$	25°C	3000±25%
Saturation magnetic flux density	$B_s$ (mT)	25°C	530
	1194A/m	100°C	425
Remanence	$B_r$ (mT)	25°C	100
		100°C	75
Coercivity	$H_c$ (A/m)	25°C	15
		100°C	12
Core loss	$P_{cv}$ (kW/m <sup>3</sup> )	0°C	380
		25°C	330
	100kHz 200mT	100°C	350
		120°C	380
Curie temperature	$T_c$ (°C)	≥225	
Electrical resistivity	$\rho$ (Ω·m)	4	



Density	$d$ (kg/m <sup>3</sup> )	4.8 × 10 <sup>3</sup>
Test core	Toroid(mm)	
	OD : 25	
	ID : 15	
	H : 7.5	

