


Bs-Temperature


H=1194A/m




Initial permeability	μ_i	25°C	3000±25%
Saturation magnetic flux density	Bs(mT)	25°C	530
Remanence	Br(mT)	25°C	100
Core loss	Pcv(kW/m³)	100°C	12
		60°C	320
		120°C	320
		140°C	380
Curie temperature	Tc(°C)		320

Electrical resistivity $\rho(\Omega\cdot m)$ 4
 Density $d(kg/m^3)$ 4.9×10^3

μ_i -Temperature



μ_i -Frequency



B-H

